

Alesta® E

Anticorrosive Primer EE Primer

EE70007711022 7110 GREY PRIMER

Anticorrosive Zinc free primer offering excellent corrosion protection on steel and aluminium substrates.



Characteristics

- Gloss Smooth
- Solid
- Corona

Usage Area

- Protection and decoration of interior parts
- Gas or liquid tanks, pipelines, structural steelwork, trucks, trailers & car parts



Approvals

GSB

908 a



- This powder coating complies with the European Directives "Restriction of the use of certain hazardous substances" 2011/65/EU and 2015/863/EU (RoHS)
- Classification A2 (non flammable) of reaction to fire in accordance with NF EN 13501-1 : 2018

The following data has been obtained under laboratory conditions as described below. Actual product properties such as gloss, colour and finish may vary depending on application conditions.



Test Conditions

- Curing Conditions (object temperature) 8 min @ 180°C
- Substrate 0,8 mm Steel Panels
- Film thickness 60 ± 10 µm

EN ISO 2360

Physical Data

- Density 1,52 g/cm³

calculated



Product Performance / Film Properties

Gloss @ 60° 85 ± 15

EN ISO 2813

Adhesion GT0

EN ISO 2409

Impact Resistance 30 inch-pound

EN ISO 6272 / ASTM D2794

Erichsen Cupping 6 mm

EN ISO 1520

Cylindrical Mandrel Bending 2 mm

EN ISO 1519




Curing Conditions (object temperature)

Can be cured using a variety of methods, e.g. IR, convection, combi ovens. In direct gas ovens, combustion by-products may cause significant colour changes (for specific advice, please contact us).

5-10 min @ 190°C

7-14 min @ 180°C

10-20 min @ 170°C



Storage Stability

24 months/35°C

Shelf life applies to materials stored in sealed plastic bags under dry and cool conditions.



Substrate Preparation

- On aluminium, steel and hot-dip galvanized steel: both chemical pre-treatment and mechanical surface preparation are compatible with Alesta® E. Surface preparation should be chosen according to type of substrate and required performance.
- The suitability of the surface preparation should be tested by the coater beforehand using appropriate test methods.



Application

- Do not mix this product with other powder coatings.
- Substrate should be correctly cleaned before use.
- Can be applied with manual or automatic guns.
- Film thickness: application settings will depend upon the geometry of the object being coated as well as the required film thickness. It is the responsibility of the applicator to make the appropriate adjustments. Certain colours should be applied at higher film thickness to ensure full coverage and therefore colour homogeneity. Below this limit, colour variation may occur due to differences in film thickness.
- Great care is taken during our manufacturing process but small variations in colour and/or appearance are unavoidable with effect colours. Therefore we recommend that a single batch of powder coating should be used to coat parts that will be subsequently assembled together. Differences are more likely with effect powder coatings such as metallic, pearlescent, speckled, textured and combinations thereof. Differences will be more easily visible on large coated parts such as cladding panels, flat sheets etc.
- Recycling of the powder: possible up to 30 % for solid colours. For special finishes (for example metallic, pearlescent, speckled), please refer to our website and the 'Metallics are us - Tips for Users' guide.



Comments

- Certain chemicals or domestic cleaning products may cause damage to the appearance of the coating. We recommend testing a small inconspicuous area first to confirm suitability.
- In instances where the coating will be subjected to additional processes (such as printing, labelling, overcoating, postforming, gluing, application of sealant or any other post-treatment), adequate testing should be performed to confirm suitability. Prototypes should be prepared under conditions that are representative of the final production process.
- Coated parts should be packed after they are fully cooled using suitable materials that are free of plasticizers. Packaged parts should be stored under cover to avoid the formation of condensation (for example under plastic wrapping film) which could result in permanent marks on the surface of the coating.
- Please contact us for specific questions.



Safety

Consult the Safety Data Sheet prior to use

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.

Copyright 2023, Axalta Coating Systems, LLC and all affiliates. The Axalta logo, Axalta™, Axalta Coating Systems™ and all products denoted with ™ or ® are trademarks or registered trademarks of Axalta Coating Systems, LLC and its affiliates. Axalta trademarks may not be used in connection with any product or service that is not an Axalta product or service.